

Bitumen grade 40/50		
	Specification	Test method
Specific gravity @25/25 C	1.01-1.06	D-70
Penetration @25 C	40/50	D-5
Softening point C	52/60	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	250min	D-92
Solubility in CS2 (wt)%	99.5 min	D-4
Spot test	negative	*A.A.S.H.O.T.102
* AMERICAN ASSOCIATION OF STATE HIGHWAY OFFICIALS		