

<b>Bitumen grade 60/70</b>		
	<b>SPECIFICATION</b>	<b>TEST METHOD</b>
<b>SPECIFIC GRAVITY @25/25 C</b>	<b>1.01-1.06</b>	<b>D-70</b>
<b>PENETRATION @25 C</b>	<b>60/70</b>	<b>D-5</b>
<b>SOFTENING POINT C</b>	<b>49/56</b>	<b>D-36</b>
<b>DUCTILITY @25 C</b>	<b>100 MIN</b>	<b>D-113</b>
<b>LOSS ON HEATING (WT)%</b>	<b>0.2 MAX</b>	<b>D-6</b>
<b>DROP IN PENETRATION AFTER HEATING %</b>	<b>20 MAX</b>	<b>D-6 &amp; D-5</b>
<b>FLASH POINT C</b>	<b>250MIN</b>	<b>D-92</b>
<b>SOLUBILITY IN CS2 (WT)%</b>	<b>99.5 MIN</b>	<b>D-4</b>
<b>SPOT TEST</b>	<b>NEGATIVE</b>	<b>*A.A.S.H.O.T.102</b>
<b>* AMERICAN ASSOCIATION OF STATE HIGHWAY OFFICIALS</b>		