

Cutback MC 70		
Characteristic	Value	Test method
Kinematic viscosity @ 60 C,cst	70-140	ASTM D-2170
Flash point (tag open-cup) C	38 min	ASTM D-3143
Water Content % vol.	0.2 max	ASTM D-95
Distillate @360 C % vol 225 C 260 C 315 C	20 max 20-60 65-90	ASTM D-402
Residue Bitumen from Distillation @ 360	55 min	ASTM D-402
Test on Residue Bitumen from Distillation		
Penetration @ 25 C	120-250	ASTM D-5
Ductility @ 25 C	100 min	ASTM D-113
Solubility in CS2 %wt	99 min	ASTM D-2042