

Oxidized bitumen 115/15

Specific gravity @ 25/25 C	1.05 approx	D-70
Penetration @ 25 C	10/20	D-5
Softening point C	110/120	D-36
Ductility @ 25 C	1.5min	D-113
Loss on heating (wt)%	0.2Max	D-6
Flash point C	260min	D-92
Solubility in CS ₂ (wt)%	99min	D-4