

Oxidized bitumen 85/25

| | | |
|----------------------------|-------------|-------|
| Specific gravity @ 25/25 C | 1.05 approx | D-70 |
| Penetration @ 25 C | 20/30 | D-5 |
| Softening point C | 80/90 | D-36 |
| Ductility @ 25 C | 1.5min | D-113 |
| Loss on heating (wt)% | 0.2Max | D-6 |
| Flash point C | 260min | D-92 |
| Solubility in CS2 (wt)% | 99min | D-4 |