

## Oxidized bitumen 90/40

Specific gravity @ 25/25 C	1.05 approx	D-70
Penetration @ 25 C	35/45	D-5
Softening point C	85/95	D-36
Ductility @ 25 C	1.5min	D-113
Loss on heating (wt)%	0.2Max	D-6
Flash point C	260min	D-92
Solubility in CS2 (wt)%	99min	D-4